

Euromix Concrete Ltd BS8500 Reinforced Applications			
Concrete	MCC	W/C	Consistence
RC20/25	240	0.7	S3
RC25/30	260	0.65	S3
RC28/35	280	0.6	S3
RC30/37	300	0.55	S3
RC32/40	300	0.55	S3
RC35/45	320	0.50	S3
RC40/50	340	0.45	S3
RC40/50 XF	340	0.45	S3
XF exposure category requires freeze/thaw resistant aggregates with a suitable MS criteria			
Please contact the Technical manager for details of availability			